




PCT

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : C03C 13/00		A1	(11) International Publication Number: WO 95/31411
			(43) International Publication Date: 23 November 1995 (23.11.95)
(21) International Application Number: PCT/EP95/01843		(81) Designated States: AU, BR, CA, CN, CZ, FI, HU, JP, KR, NO, NZ, PL, SI, SK, US, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE).	
(22) International Filing Date: 16 May 1995 (16.05.95)			
(30) Priority Data: P 44 17 231.1 17 May 1994 (17.05.94) DE 195 03 172.5 1 February 1995 (01.02.95) DE		Published With international search report.	
(71) Applicant (for all designated States except US): ISOVER SAINT-GOBAIN [FR/FR]; Les Miroirs, 18, avenue d'Alsace, F-92400 Courbevoie (FR).			
(72) Inventors; and (75) Inventors/Applicants (for US only): LOHE, Peter [DE/DE]; Rüterstrasse 5, D-67112 Mutterstadt (DE). HOLSTEIN, Wolfgang [DE/DE]; Herderstrasse 2, D-35315 Homberg (DE). SCHWAB, Wolfgang [DE/DE]; Schönaauer Strasse 25, D-68723 Plankstadt (DE).			
(74) Agent: KADOR & PARTNER; Corneliusstrasse 15, D-80469 Munich (DE).			

(54) Title: A MINERAL-FIBER COMPOSITION



(57) Abstract

A biologically degradable mineral-fiber composition characterized by the following constituents in percent by weight: SiO₂ 50 to 65, Al₂O₃ less than 2, CaO 16 to 30, MgO 4 to 15, Na₂O 8 to 20, K₂O 0 to 2, B₂O₃ 0 to 10, TiO₂, Fe₂O₃, Cr₂O₃, BaO, MnO, P₂O₅ 0 to 5.

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	GB	United Kingdom	MR	Mauritania
AU	Australia	GE	Georgia	MW	Malawi
BB	Barbados	GN	Guinea	NE	Niger
BE	Belgium	GR	Greece	NL	Netherlands
BF	Burkina Faso	HU	Hungary	NO	Norway
BG	Bulgaria	IE	Ireland	NZ	New Zealand
BJ	Benin	IT	Italy	PL	Poland
BR	Brazil	JP	Japan	PT	Portugal
BY	Belarus	KE	Kenya	RO	Romania
CA	Canada	KG	Kyrgyzstan	RU	Russian Federation
CF	Central African Republic	KP	Democratic People's Republic of Korea	SD	Sudan
CG	Congo	KR	Republic of Korea	SE	Sweden
CH	Switzerland	KZ	Kazakhstan	SI	Slovenia
CI	Côte d'Ivoire	LI	Liechtenstein	SK	Slovakia
CM	Cameroon	LK	Sri Lanka	SN	Senegal
CN	China	LU	Luxembourg	TD	Chad
CS	Czechoslovakia	LV	Latvia	TG	Togo
CZ	Czech Republic	MC	Monaco	TJ	Tajikistan
DE	Germany	MD	Republic of Moldova	TT	Trinidad and Tobago
DK	Denmark	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	US	United States of America
FI	Finland	MN	Mongolia	UZ	Uzbekistan
FR	France			VN	Viet Nam
GA	Gabon				

A mineral-fiber composition

The present invention relates to a mineral-fiber composition that is biologically degradable.

The prior art describes some mineral-fiber compositions which are said to be biologically degradable.

The biological degradability of mineral-fiber compositions is of great importance because various studies point out that mineral fibers with very small diameters in the range of less than 3 microns are suspected to be carcinogenic, while biologically degradable mineral fibers of such dimensions show lower or no carcinogenicity.

However not only the biological degradability is of crucial importance but also the mechanical and thermal properties of the mineral fibers, or the products produced therefrom, and the processibility of the mineral-fiber composition. For example mineral fibers are used to a great extent for insulation purposes. In particular for this application in the industrial area sufficient temperature stability of the mineral fibers is necessary.

Also, the mineral-fiber composition must permit processibility by known methods for producing mineral fibers with a small diameter, for example the jet process.

The invention is based on the problem of providing a novel mineral-fiber composition that is characterized by biological degradability, has good temperature stability and is easy to process.

The invention is based on the finding that this problem can be solved by a mineral-fiber composition that is built up substantially from silicon oxide, calcium oxide, magnesium oxide and sodium oxide.

It has turned out that such a mineral-fiber composition fulfills the combination of the necessary properties, namely biological degradability, temperature stability and good processibility.

- 2 -

The object of the invention is a mineral-fiber composition that is biologically degradable, characterized by the following constituents in percent by weight:

SiO ₂	50 to 65
Al ₂ O ₃	less than 2
CaO	16 to 30
MgO	4 to 15
Na ₂ O	8 to 20
K ₂ O	0 to 2
B ₂ O ₃	0 to 10
TiO ₂ , Fe ₂ O ₃ , Cr ₂ O ₃ , BaO, MnO, P ₂ O ₅	0 to 5

The inventive mineral-fiber compositions are drawable by the jet process or the rotary process. The obtained fibers have good temperature stability. Surprisingly enough, the mineral-fiber compositions show biological degradability. The mean fiber diameter is preferably 10 microns or less, and especially between 2.5 and 5 microns.

The inventive mineral-fiber compositions preferably have the following constituents in percent by weight:

SiO ₂	55 to 60
Al ₂ O ₃	less than 1.5
CaO	16 to 25
MgO	5 to 15
Na ₂ O	9 to 15
K ₂ O	less than 2
B ₂ O ₃	0 to 8
TiO ₂ , Fe ₂ O ₃ , Cr ₂ O ₃ , BaO, MnO, P ₂ O ₅	0 to 5

In particular, the inventive mineral-fiber compositions have the following constituents in percent by weight:

SiO ₂	55 to 59
Al ₂ O ₃	less than 1.5
CaO	18 to 23
MgO	8 to 12
Na ₂ O	9 to 13
K ₂ O	less than 1
B ₂ O ₃	0 to 3
TiO ₂ , Fe ₂ O ₃ , Cr ₂ O ₃ , BaO, MnO, P ₂ O ₅	0 to 3

The content of magnesium oxide is preferably 6 to 12 percent by weight and in particular 8 to 12 percent by weight.

The content of chromium oxide is preferably less than 1.5 percent by weight and in particular less than 1.0 percent by weight.

The content of boron oxide is preferably less than 4 percent by weight.

To assess biological degradability the standard powder test of the German Glass Society was used. This is an easily conducted method and gives a sufficient measure of biological degradability. The method is described in L. Springer, "Laboratoriumsbuch für die Glasindustrie", 3rd edition, 1950, Halle/S: W. Knapp Verlag.

The temperature behavior of the mineral fibers was determined by the Swedish method. In this method a silit tube furnace is used with a horizontal working tube open on both sides having a length of 350 mm and an inside diameter of 27 mm. In the center of the furnace there is a small ceramic supporting plate (30 X 20 X 3 mm) for holding the test sample. The test sample has dimensions of 12 X 12 X 12 mm or 12 mm ϕ X 12 mm height. The bulk density is normally 100 kg/m³. The temperature increase is 5 K/min. The change in test sample height is determined continuously with a reading optic.

The invention shall be described in more detail in the following with reference to examples.

Example 1

A mineral wool of the following composition in percent by weight was produced:

SiO ₂	56
Al ₂ O ₃	0.5
CaO	20
MgO	10
Na ₂ O	10
B ₂ O ₃	2.7

This composition could be processed well to mineral fibers with a mean diameter of 2.5 microns by the jet process at a drawing temperature of 1330°C.

An investigation according to the standard powder test of the German Glass Society yielded a value of 35 mg/kg and thus a value for high biological degradability.

Determination of temperature behavior by the Swedish method yielded a temperature stability at 5% reduction in height of 620°C, which can be clearly seen from the corresponding diagram shown by way of example in the single drawing.

Example 2

A mineral wool with the following composition in percent by weight was produced:

	<u>% by weight</u>	<u>Mole %</u>
SiO ₂	56	52.75
Al ₂ O ₃	1.0	0.55
CaO	21	21.20
MgO	11	15.45
Na ₂ O	11	10.05

This composition could be processed well to mineral fibers with a mean diameter of 2.7 microns by the jet process at a drawing temperature of 1310°C.

An investigation according to the standard powder test of the German Glass Society yielded a value of 37 mg/kg and thus a value for high biological degradability.

Determination of temperature behavior by the Swedish method yielded a temperature stability at 5% reduction in height of 600°C.

Claims

1. A mineral-fiber composition that is biologically degradable, characterized by the following constituents in percent by weight:

SiO ₂	50	to 65
Al ₂ O ₃	less than 2	
CaO	16	to 30
MgO	4	to 15
Na ₂ O	8	to 20
K ₂ O	0	to 2
B ₂ O ₃	0	to 10
TiO ₂ , Fe ₂ O ₃ , Cr ₂ O ₃ , BaO, MnO, P ₂ O ₅	0	to 5

2. The mineral-fiber composition of claim 1, characterized by the following constituents in percent by weight:

SiO ₂	55	to 60
Al ₂ O ₃	less than 1.5	
CaO	16	to 25
MgO	5	to 15
Na ₂ O	9	to 15
K ₂ O	less than 2	
B ₂ O ₃	0	to 8
TiO ₂ , Fe ₂ O ₃ , Cr ₂ O ₃ , BaO, MnO, P ₂ O ₅	0	to 5


3. The mineral-fiber composition of claim 1, characterized by the following constituents in percent by weight:

SiO ₂	55	to 59
------------------	----	-------

Al_2O_3	less than 1.5
CaO	18 to 23
MgO	8 to 12
Na_2O	9 to 13
K_2O	less than 1
B_2O_3	0 to 3
$\text{TiO}_2, \text{Fe}_2\text{O}_3, \text{Cr}_2\text{O}_3, \text{BaO}, \text{MnO}, \text{P}_2\text{O}_5$	0 to 3

4. The mineral-fiber composition of any of claims 1 to 3, characterized in that the content of boron oxide is less than 4 percent by weight.

1/1



INTERNATIONAL SEARCH REPORT

International Application No

PCT/EP 95/01843

A. CLASSIFICATION OF SUBJECT MATTER
IPC 6 C03C13/00

According to International Patent Classification (IPC) or to both national classification and IPC:

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
IPC 6 C03C

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	WO,A,89 12032 (MANVILLE SALES CORPORATION) 14 December 1989 see page 5 - page 6; example 225 ---	1-4
A	FR,A,2 690 438 (ISOVER SAINT-GOBAIN) 29 October 1993 see claim 1; example 2 ---	1-4
A	WO,A,92 09536 (PAROC OY AB) 11 June 1992 see claims -----	1-4

☐ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents:

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *I* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

- *T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- *&* document member of the same patent family

Date of the actual completion of the international search

9 August 1995

Date of mailing of the international search report

31. 08. 95

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+ 31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+ 31-70) 340-3016

Authorized officer

Van Bommel, L

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No
PCT/EP 95/01843

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
WO-A-8912032	14-12-89	AU-A- 3765789 US-A- 5332699	05-01-90 26-07-94
FR-A-2690438	29-10-93	AU-B- 4263293 BR-A- 9305492 CA-A- 2110998 CN-A- 1078708 CZ-A- 9302865 EP-A- 0596088 WO-A- 9322251 HU-A- 67212 JP-T- 6508600 NO-A- 934725 SI-A- 9300218	29-11-93 11-10-94 11-11-93 24-11-93 19-10-94 11-05-94 11-11-93 28-03-95 29-09-94 20-12-93 31-12-93
WO-A-9209536	11-06-92	FI-B- 93346 AT-T- 117662 AU-A- 8908791 DE-D- 69107091 EP-A- 0558548	15-12-94 15-02-95 25-06-92 09-03-95 08-09-93